## **AMENDMENTS TO THE CLAIMS**

The following listing of claims replaces all prior versions and listings of claims in the application:

- 1. (Currently amended) A coating composition consisting of: a [[₩]]waterthinnable polyurethane with at least two free OH groups obtained from the reactions consisting of: a first conversion of a primary and/or secondary alkanolamine with a NCO compound giving an intermediate product, followed by the addition of a cyclic carboxylic anhydride to the intermediate product; wherein the NCO compound has at least one free NCO group and no blocked NCO group, and the NCO compound is obtained by reacting at least one polyol with at least one polyisocyanate, in which the polyol is saturated polyester polyol or saturated polyether polyol; all alkanolamine being converted during the first conversion to the intermediate product such that the nitrogen atom of the alkanolamine reacts with one of the free NCO groups of prepolymers the NCO compound to form a urea bond; and the cyclic carboxylic anhydride reacting, with ring opening, with the OH group, originating from the alkanolamine, of the intermediate product[[-]] and wherein the coating composition further consists of a crosslinking agent that is reactive with the water-thinnable polyurethane.
- 2. (Currently Amended) The coating composition Water-thinnable polyurethane according to claim 1 wherein the NCO compound does not exhibit any OH group.
- 3. (Currently Amended) <u>The coating composition Water-thinnable</u> polyurethane according to claim 1 wherein the NCO compound is modified by at least one alkoxypoly(oxyalkylene) alcohol.

- 4. (Currently Amended) The coating composition Water-thinnable polyurethane according to claim 1 wherein the NCO compound is a prepolymer.
- 5. (Currently Amended) The coating composition Water-thinnable polyurethane according to claim 1 wherein the NCO compound exhibits at least two free NCO groups.
- 6. (Currently Amended) The coating composition-Water-thinnable polyurethane according to claim 1 wherein at least one OH group of the alkanolamine is linked with its nitrogen atom via a substituted or non-substituted alkyl group with 2 to 6 carbon atoms in the main chain.
- 7. (Currently Amended) The coating composition-Water-thinnable polyurethane according to claim 1 wherein OH groups originating from the alkanolamine are fully or partially secondary.
- 8. (Currently Amended) <u>The coating composition-Water-thinnable polyurethane</u> according to preceding claims characterised in that claim 1 wherein alkanolamine is diethanolamine and/or diisopropanolamine.
- 9. (Currently Amended) The coating composition—Water-thinnable polyurethane according to claim 1 wherein it has an acid number of at least 10 mg KOH/g, in particular of at least 20 mg KOH/g.
- 10. (Currently Amended) The coating composition Water-thinnable polyurethane according to claim 1 wherein the polyurethane has a number average molecular weight of between 500 and 10,000, in particular between 1,000 and 4,000.
- 11. (Currently Amended) <u>The coating composition</u>—Water-thinnable polyurethane according to claim 1 wherein the cyclic carboxylic anhydride is selected from the group of phthalic anhydride, hexahydrophthalic anhydride,

tetrahydrophthalic anhydride, methyl hexahydrophthalic anhydride, succinic anhydride and maleic anhydride.

- 12. (Currently amended) <u>The coating composition</u> Water-thinnable polyurethane according to claim 1 wherein the cyclic carboxylic anhydride is trimrllitictrimellitic anhydride.
- 13. (Currently Amended) The coating composition according to claim 1 wherein the crosslinking agent comprises a melamine resin A method, comprising contacting a water-thinnable polyurethane according claim 1 with a melamine resin for the production of hot curing coating compositions.
- 14. (Currently Amended) The coating composition according to claim 13 wherein A method, comprising contacting a water-thinnable polyurethane according to claim 13 characterised in that the melamine resin is a highly alkylated melamine resin.
- 15. (Currently Amended) The coating composition according to claim 14 A method according to claim 14 wherein the melamine resin is one without NH groups.
- 16. (Currently Amended) The coating composition according to claim wherein A method according to claim 13 wherein the crosslinking temperature of the coating composition is less than 145°C.
- 17. (Currently Amended) The coating composition according to claim wherein A method according to claim 13 wherein the crosslinking temperature of the coating composition is more than 180°C.
- 18. (Canceled)
- 19. (Currently Amended) <u>The coating composition</u> Water-thinnable polyurethane according to claim 2 wherein the NCO compound is modified by at least one alkoxypoly(oxyalkylene) alcohol.

20. (Currently Amended) The coating composition A method according to claim 15 wherein the melamine resin is hexamethoxymethyl melamine.